



3d Finite Element Modelling of Non-Crimp Fabric Based Fibre Composite Based on X-Ray Ct Data

Jespersen, Kristine Munk; Asp, Leif; Mikkelsen, Lars Pilgaard

Published in:

Proceedings of the 30th Nordic Seminar on Computational Mechanics (NSCM-30)

Publication date:

2017

Document Version

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Jespersen, K. M., Asp, L., & Mikkelsen, L. P. (2017). 3d Finite Element Modelling of Non-Crimp Fabric Based Fibre Composite Based on X-Ray Ct Data. In J. Hørsberg, & N. L. Pedersen (Eds.), *Proceedings of the 30th Nordic Seminar on Computational Mechanics (NSCM-30)* (pp. 90)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

3D FINITE ELEMENT MODELLING OF NON-CRIMP FABRIC BASED FIBRE COMPOSITE BASED ON X-RAY CT DATA

KRISTINE M. JESPERSEN^{*}, LEIF ASP[†] AND LARS P. MIKKELSEN^{*}

^{*} Department of Wind Energy
Technical University of Denmark
Risø Campus, Fredriksborgvej 399, 4000 Roskilde, Denmark
e-mail: kmun@dtu.dk, lapm@dtu.dk, web page: <http://www.vindenergi.dtu.dk/>

[†] Department of Industrial and Materials Science
Chalmers University of Technology
Hörsalsvägen 7A, 412 58 Göteborg, Sweden
Email: leif.asp@chalmers.se - Web page: <http://www.chalmers.se>

Abstract. Due to the high number of fatigue load cycles during the life of a wind turbine blade, fatigue is one of the main design concerns. However, it is still not possible to realistically predict the fatigue life of the non-crimp fabric based fibre composites commonly used for the main load carrying parts of wind turbine blades. Existing modelling attempts generally consider the fibre bundle structure as a perfect pattern, however recent experimental X-ray CT studies [1,2] have shown that the local variations in the fibre bundle structure have a large influence on the observed fatigue damage initiation and progression in the material. In the current study, the real bundle structure inside a non-crimp fabric based fibre composite is extracted from 3D X-ray CT images and imported into ABAQUS for numerical modelling. The local stress concentrations when loaded in tension caused by the fibre bundle structure are examined and compared to experimental observations of the fatigue damage. In the current study the bundle structure is manually segmented, however the possibility of automatic segmentation in the future is also discussed. The study shows the potential of X-ray CT based modelling for increased understanding of the fatigue damage mechanisms, but also sets the stage for modelling across scales including the variations caused by manufacturing process.

Keywords: Non-crimp fabric based composite, X-ray CT based modelling, Finite element modelling, Fatigue damage.

REFERENCES

- [1] Zangenberg, J., Brondsted, P., & Gillespie, J. W., “Fatigue damage propagation in unidirectional glass fibre reinforced composites made of a non-crimp fabric”, *Journal of Composite Materials*, **48**(22), 2711–2727 (2014).
- [2] Jespersen, K. M., Zangenberg, J., Lowe, T., Withers, P. J., & Mikkelsen, L. P., “Fatigue damage assessment of uni-directional non-crimp fabric reinforced polyester composite using X-ray computed tomography”, *Composites Science and Technology*, **136**, 94–103 (2016).